

## FDA Compliant EPDM 60° Shore 'A'

### Quality: 4660

#### Approvals:

- 3-A Hygiene standards, cl. III
- FDA Compliant
- Physiologically safe
- Sulphur-Cured, silicone-free
- Complies with EU Directives 1935/2004 and 2023/ 2006
- Phthalate Free
- RoHS 2011/65/EU Conform
- 2003/11/EC Conform
- REACH EC: 1907/2006 Conform
- SVHC Conform



Food Safety  
EC No. 1935/2004



PROPERTY	TYPICAL VALUE	TEST METHOD
Colour	White	
Hardness	55 - 60° Shore 'A'	DIN ISO 7619-1
Density	1.16 g.cm <sup>3</sup>	-
Elongation @ Break	550%	DIN 53504
Compression Set - 24hrs at 70°C	30%	ISO 815
Tear Resistance	25 N/mm	DIN 53507
Tensile Strength	11 MPa	ASTM D412C
Temperature Range	-25°C to +100°C	

**Dimensional Tolerances:** are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

**Disclaimer:** All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

**J-FLEX Rubber Products**

Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 email: [sales@j-flex.com](mailto:sales@j-flex.com) web: [www.j-flex.com](http://www.j-flex.com)

