

MATERIAL DATA SHEET



FDA COMPLIANT SILICONE RUBBER SHEETING 60° SHORE 'A'

White (W049): Translucent (T050): Red (R089): Black (B60):
Blue (B62) – Colour Match No. CM435

PROPERTY	TEST METHOD	UNITS	SPECIFICATION LIMITS	TYPICAL VALUE
HARDNESS	ASTM D2240 DIN ISO 7619-1	°SHORE A	60° (+/-5)	60
TENSILE STRENGTH	ISO 37 type 1 ASTM D412 Die C DIN 53504 type S1	MPa	7.0 min	10
			1015 min	1450
ELONGATION @ BREAK	ISO 37 type 1 ASTM D412 die C DIN 53504 type S1	%	280 min	400
TEAR STRENGTH	ASTM D624 die B	N/mm lb/in	12.5 min 71.4 min	22 125
COMPRESSION SET 24hrs @ 150°C 22hrs @ 300°F	BS 903 pt A6 type B DIN/ISO 815 type B ASTM D395 method B type 2	%	30 max	13
			30 max	10
TEMPERATURE RANGE	-60°C to +230°C (Continuous)		+250°C (Intermittent)	
GENERAL THICKNESSES	0.3, 0.5, 0.8, 1.0, 1.5, 2.0, 3.0, 4.0, 5.0, 6.0, 8.0, 10.0 & 12.0mm (Check with our Sales Office for specific availability)			

All Silicone sheet products supplied by J-Flex comply with these regulations:-



Food Safety
EC No. 1935:2004

ISSUE 15: January 2015

Continued



J-FLEX

High Performance Elastomer Sheetings & Manufactured Components

Units 1 & 2, London Road Business Park, Retford,
Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712 400 fax: +44 (0) 1777 712 409
www.j-flex.co.uk



GENERAL CHARACTERISTICS		
TEST	RESULT	STANDARD
Brittle Point	-80°C (-112°F)	ASTM D746
Limiting Oxygen Index	24.0%	BS 2782 Part 1
Thermal Conductivity	0.24 W.m ⁻¹ .K ⁻¹	VDE 0304
Dielectric Strength	23 kV.mm ⁻¹	VDE 0303
Dielectric Constant	2.9	VDE 0303
Dissipation Factor	3x10 ⁻⁴	VDE 0303
Volume Resistivity	3x10 ¹⁵ Ω.cm	VDE 0303
Radiation Resistance	>10 ⁵ Grays (10 ⁷ Rads) typical	
Coefficient of Thermal Expansion	Between 300 and 250x10 ⁻⁶ cm/cm/°C (Typical range)	

These sheetings have been fully post cured and all the ingredients used to produce these sheetings are listed in FDA 21 CFR 177. 2600.

We manufacture our FDA materials in accordance with FDA guidelines set out in 21 CFR 177.2600 and the manufactured materials have been tested to, and comply with the tests listed in 21 CFR 177.2600 (d) to (h).

This makes them suitable for contact with dry, aqueous and fatty foods defined by the FDA.

As stated in 21 CFR 177.2600 it is recommended that the manufactured article is thoroughly cleansed prior to first use in contact with food. Empfehlung and colour bleed test according to BfR Empfehlung part B 11 & Directive EC 1935/2004.

We confirm that our Silicone Products are carefully produced to comply with European Commission Regulations (EC)2023/2006 “good manufacturing practice for materials and articles intended to come into contact with food”.

These products meet the flammability requirements of FAR 25/JAR/CS 25 Appendix F, Part 1, (a)(1)(iv) & (a)(1)(v) horizontal flammability tests and Automotive Standard PART 571FMVSS302.

WRAS APPROVAL NO: 1310541 (pending reapproval): Approved for cold & hot potable water use up to 85°C in accordance to BS 6920.

ISSUE 15

January 2015

