

Nitrile (NBR) / Nylon Diaphragm Sheet

Suitable for LPG, CNG, mineral oils, water

CODE: TX1B1N4040 Nylon Fabric 210 coated black NBR. Thickness 0.40mm		
ELASTOMER CHARACTERISTICS	TYPICAL VALUES	TEST METHOD
Elastomer	Nitrile Rubber (NBR)	
Hardness	70° (+/-5°) Shore 'A'	
Colour	Black	
FABRIC CHARACTERISTICS	TYPICAL VALUES	TEST METHOD
Fabric	PA 210 (235dTex)	
Weight	110 (+/-5) g/m ²	
Thickness	0.20 (+/-0.01)	
COATED FABRIC CHARACTERISTICS	TYPICAL VALUES	TEST METHOD
Thickness	0.40 (+/-0.04)	UNI EN ISO 2286-3
Weight	450 (+/-10%) g/m ²	UNI EN ISO 2286-2
Tensile Strength - Warp Tensile Strength - Weft	≥ 1000 N/5cm ≥ 1000 N/5cm	UNI EN ISO 1421 UNI EN ISO 1421
Elongation @ Break - Warp Elongation @ Break - Weft	≥ 20% ≥ 20%	UNI EN ISO 1421 UNI EN ISO 1421
Adhesion	≥ 20 N/cm	
Temperature Range	-20°C to +100°C	

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

J-FLEX Rubber Products



Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409 email: sales@j-flex.com web: www.j-flex.com

