



Viton™ /FKM Sponge Sheeting

A closed cell formulation that is manufactured with a continuous skin on both sides. The skin makes the sheet stronger and more tear resistant and even when the surface skin is punctured or cut, the sheets will not allow the passage of air or fluid between cells. The non-absorbent sheets are highly compressible, resilient, lightweight and provide good thermal insulation.

Like dense Viton™, J-Flex Viton™ Sponge is generally resistant to aliphatic and aromatic hydrocarbons, oils, fuels, ozone and weather, lubricants, and animal or vegetable oils. It is also resistant to acids and hot water.

J-Flex Viton™ Sponge sheets have a service temperature of -25°C to 204°C, however, elevated temperatures while under compression will have an adverse effect on the resilience of this material.

TYPICAL PHYSICAL PROPERTIES				
Thickness	1/8" (3.18mm)	1/4" (6.35mm)	3/8" (9.53mm)*	1/2" (12.7mm)*
Water Pick-Up (% weight increase)	0.00%	0.02%	0.06%	0.01%
Compression Set (%)				
22hrs @ 75°C	27%	13%	14%	17%
22hrs @ 158°C	100%	100%	100%	100%
Low Temperature Brittleness (°F)	-10°F	-10°F	-10°F	-10°F
Compression Deflection (psi)				
25% Deflection - original	6.5	5.5	4.0	3.5
25% Deflection - 7 days @ 400°F	9.0	7.5	6.0	5.0
Density - Lbs per cubic foot	19	17	15	10
Thickness Tolerance (inches)	+0.050 -0.030	+0.060 -0.060	+0.080 -0.080	+0.125 -0.125

Dimensional Tolerances: E3 as standard. E2 and E1 available on request.

Availability - in Sheets:

3.18mm thick (1/8")

609mm (24") x 1219mm (48")
711mm (28") x 1422mm (56") EX-STOCK

6.35mm thick (1/4")

609mm (24") x 1219mm (48")
762mm (30") x 1422mm (56") EX-STOCK

9.53 mm thick (3/8")

762mm (30") x 1422mm (56")

12.7 mm thick (1/2")

762mm (30") x 1422mm (56")



Viton™

Viton™ is the registered trademark of The Chemours Chemical Company

Partner of Viton™ a Brand of the Chemours Company

J-Flex are an approved Chemours Viton™ licensee

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

J-FLEX Innovative Rubber Solutions



Certificate No. RS 27920



Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409 email: sales@j-flex.com web: www.j-flex.com