

EPDM 25° Shore 'A'

Characteristics & Features:

- Very soft EPDM material, sulphur cross-linked
- Extremely high elongation
- Nitrosamine free
- PAK-Free in accordance with Directives 2005/69/EG

PROPERTY	TEST METHOD	VALUES
Hardness	DIN ISO 7619 -1	20 - 30 Shore 'A'
Colour		Black
Density		1.00 g/cm ³
Elongation at Break	DIN 53504	487%
Rebound Resilience		55%
Compression Set	DIN 53517	25% Compress, 3d, RT = 6.9% 25% Compress, 24hr, 70°C = 13.3
Tensile Strength	DIN 53504	5.5 MPa
Tear Resistance: Strip Test	DIN ISO 34-1 ASTM 624 D	3.8 N/mm 38.9 N/mm
Abrasion	DIN 53 516	154 mm ³
Spec. Volume Resistance	DIN IEC 60093	2.0 x 10 ¹⁴ Ohm x cm
Surface Resistance	DIN EN 100 015/1	10 ¹² Ohm
Fire Behaviour	FMVSS302	33.3mm/min
Cold, 24hr, -45°C	DIN 53 545	i.O.
Ageing 72hr, 70°C - Shore Hardness A Ageing 72hr, 70°C - Tear Resistance Ageing 72hr, 70°C - Elongation @ Break	DIN 53508/ISO 188	-1 +18.2% +5.3%
Temperature Range	-45°C to +100°C (up to 110°C Intermittent)	

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

J-FLEX Rubber Products

Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409 email: sales@j-flex.com web: www.j-flex.com

