

## EPDM Rubber 60° Shore 'A'

### Quality: JFEP760A

PROPERTY	TEST METHOD	VALUES
Hardness	DIN 53505	60°+/-5° Shore 'A'
Specific Weight	DIN 53479	1.12 +/-0.02 g/cm <sup>3</sup>
Tensile Strength	DIN 53504	8.0 N/mm <sup>2</sup> (min)
Elongation	DIN 53 504	350% (min)
Compression set 25% compression, 22hrs 70°C	ISO 815	43%
Ageing (hardness/tensile strength/ elongation) - 70hrs 70°C	DIN 53508	+1 Shore A / -2 % / -4 %
Colour	Black	
Temperature Resistance	- 40° up to +110°C	
Availability	Rolls: 1200mm wide x 0.5mm Thick (+/-0.1)	
Surface Finish	Smooth Finish and Talced	
Properties	Acid and alkaline resistant, ozone and weather resistant	

**Dimensional Tolerances:** are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

**Disclaimer:** All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

**J-FLEX Rubber Products**

Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409 email: sales@j-flex.com web: www.j-flex.com

