

FKM 75 High Tensile with PTFE Sheet

Thickness of PTFE film is 0.1 - 0.2 mm

PROPERTIES	VALUES
Elastomer	FPM/FKM
Hardness	75° (±5°) Shore 'A'
Colour	Black
Tensile Strength	≥ 8 MPa
Elongation @ Break	≥ 200% (±50%)
Compression Set after 22hrs @ 200°C	≤ 45% (max)
Temperature Range	-10°C to +170°C

Other Features:

- Very good resistance to weathering, ozone, chemical media, oil and gasoline.
- Very good heat resistance.

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

J-FLEX Rubber Products

Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409 email: sales@j-flex.com web: www.j-flex.com



Certificate No. RS 27920

