



Viton™ B Rubber Sheeting

Colour: Black Viton™'B' Compound - 68% Fluorine content

PROPERTIES	STANDARD	VALUES
Hardness	DIN53505, ASTM D2240	75° (±5°) Shore 'A'
Tensile Strength	DIN53504 die S1, ASTM D412 die C	≥ 12 MPa
Elongation @ Break	DIN53504 die S1, ASTM D412 die C	≥ 180%
Compression Set after 22hrs @ 200°C	ASTM D395 Method B	≤ 45% (max)
Density		1.9 (±0.1)
Working Temperature		-10 to +250°C



Viton™ and any associated logo is a trademark or copyright of THE CHEMOURS COMPANY FC, LLC and used under license by Clockpress Ltd t/a J-Flex Rubber Products.

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

J-FLEX Innovative Rubber Solutions

Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409 email: sales@j-flex.com web: www.j-flex.com

