FDA Compliant Solid Silicone Elastomer Rolls

Our general-purpose range of silicone rolls.

The range has been tested to and is in compliance with the American Food and Drugs Administration (FDA) 21 CFR 177-2600, BfR XV Empfehlung and colour bleed test according to BfR-Empfehlung part B 11 & Directive EC 1935/2004. Also Flame Retardant: UL94HB FAR25/JAR25 (in grey colour only)

Translucent, Blue, White, Red and Black 40° to 70° Shore have been approved by WRAS (Water Regulation Advisory Service) for use with potable water at temperatures up to 85°C (185°F) - Listing number: 2011556.

Additional compliance:

These products meet the flammability requirements of FAR 25/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(iv) and (a)(1)(v) horizontal flammability tests and Automotive Standard PART 571FMVSS302.

Environmental Resistance:

Silicone rubber products have an excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmic radiation, ionising radiation and weathering in general.









Temperature Range:

-60°C (-76°F) to +230°C (+446°F) and up to 250°C (482°F) intermittent.

Availability:

- · Widths of 1200mm (standard), 1500mm and 1800mm.
- · Pressure sensitive adhesive backing.
- · Custom cut gaskets.
- · Standard colours: Blue. White, Red, Black, White.
- · Translucent available at extra cost.
- · Flame retardant in Grey only.
- · Capability to colour match.

| | | JFGP30* | JFGP40 | JFGP50 | JFGP60 | JFGP70 | JFGP80* | |
|---------------------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------------------|
| PROPERTY | UNITS | TYPICAL VALUE | TYPICAL VALUE | TYPICAL VALUE | TYPICAL VALUE | TYPICAL VALUE | TYPICAL VALUE | TEST METHOD |
| Hardness | Shore A (±5) | 30 | 40 | 50 | 60 | 70 | 80 | ISO 48-4 |
| Tensile Strength | MPa psi | 8.0 1160 | 9.0 1305 | 9.0 1305 | 10.0 1450 | 10.0 1450 | 8.0 1160 | ISO 37 type 2 |
| Elongation to Failure | % | 550 | 525 | 450 | 400 | 320 | 300 | ISO 37 type 2 |
| Tear Strength | N/mm (ib/in.) | 16.0 91 | 23 130 | 20 114 | 22 125 | 20 115 | 20 114 | ASTM D624 die B |
| Compression Set 24 hours @150°C | % | 23 | 25 | 15 | 13 | 9 | 18 | ISO 815 type B |
| Compression Set 22 hours @300°C | % | 20 | 22 | 16 | 10 | 10 | 16 | ASTM D395 method B type 2 |

^{*30°} and 80° Shore are not currently WRAS approved. The WRAS listing number for 40 to 70 Shore is 2011556.

Standard stock offering is 60° Shore, in thicknesses 0.3mm to 12mm (other thicknesses to order) For 40° translucent: our standard stock offerings are thicknesses 1mm to 10mm

continued on page 2

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.



Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom tel: +44 (0) 1777 712400 email: sales@j-flex.com web: www.j-flex.com





FDA Compliant Solid Silicone Elastomer Rolls

| TEST | RESULT | STANDARD | |
|-----------------------|---|----------------|--|
| Brittle Point | -80°C (-112 °F) | ASTM D746 | |
| Limiting Oxygen Index | 24.0% | BS 2782 Part 1 | |
| Thermal Conductivity | 0.24 W.m ⁻¹ .K ⁻¹ | VDE 0304 | |
| Radiation Resistance | >10₅ Grays (10₂ Rads) typical | | |

Dimensional Tolerances:

| THICKNESS (mm) | ST2 | | |
|----------------|-------|--|--|
| 0 - 1 | ±0.2 | | |
| 1 - 1.6 | ±0.25 | | |
| 1.6 - 2.5 | ±0.35 | | |
| 2.5 - 4 | ±0.4 | | |
| 4 - 6.3 | ±0.5 | | |
| 6.3 - 10 | ±0.7 | | |
| 10 - 16 | ±0.8% | | |

Dimensional Tolerances: are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

Disclaimer: All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.



Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom tel: +44 (0) 1777 712400 email: sales@j-flex.com web: www.j-flex.com



