

# FPM/FKM Sheet 75° Shore

## FDA Compliant Sheeting

### Features:

- FPM/FKM 66% Fluorine Content
- Bisphenol Cured
- Post Cured
- Applicable to +275°C for a short time

### Available in thicknesses: 0.5mm to 25mm

0.5mm to 6mm - Rolls: 1200mm wide x 10m long  
 8mm & 10mm - Rolls: 1200mm wide x 5m long  
 Over 10mm thick - plates: 2000mm x 1000mm

**Colour:** Black

### Other Features:

- Very good resistance to weathering, ozone, chemicals, media, oil and gasoline.
- Very good heat resistance.

PROPERTY	TYPICAL VALUES	TEST METHOD
Type	'A' Type Di-Polymer	-
Hardness	75° (+/-5°) Shore 'A'	ASTM D2240
Tensile Strength	≥ 9 Mpa	ASTM D412
Elongation @ Break	≥ 180%	ASTM D412
Compression Set 22hrs@200°C	≤ 30%	ASTM D395 - method 'B'
Temperature Resistance	-10°C to +230°C	

FLUOR-A-COM® is a registered trade mark of J-Flex Rubber Products



**Dimensional Tolerances:** are typically class 3 as standard, unless otherwise stated. Class 2 and Class 1 tolerances on request, in most instances.

**Disclaimer:** All recommendations and information contained in this specification sheet are to the best of our knowledge correct. Since conditions of service are beyond our control, users must satisfy themselves that the products are suitable for intended use. No warranty is given or implied in respect of information or recommendations or that any use of products will infringe rights belonging to other parties. In any event or occurrence our liability is limited to the invoice value of our goods delivered to you. We reserve the right to change product design and properties without notice.

**J-FLEX Rubber Products**

Units 1 & 2, London Road Business Park, Retford, Nottinghamshire, DN22 6HG, United Kingdom

tel: +44 (0) 1777 712400 email: sales@j-flex.com web: www.j-flex.com

